
The RILEM Approach to Mitigate Alkali Aggregate Reactions (AAR) in Concrete

RILEM Technical Committee (TC) 258-AAA (2014–2019) Avoiding Alkali Aggregate Reactions in Concrete. Performance Based Concept.

Børge Johannes Wigum (Chairman) Jan Lindgård (Secretary)









RILEM Technical Committees (TCs) on AAR

- O TC 106 (1988–2001) Accelerated Aggregate Tests
- \bigcirc TC 191-ARP (2001–2006) Diagnosis/Appraisal & Specification
- O TC 219-ACS (2006–2014) Performance Testing & Modelling




Dr Philip Nixon – Chairman Dr Ian Sims – Secretary



International Union of Laboratories and Experts in Construction Materials, System and Structures





RILEM TC 258 AAA (2014-2019)



- O WP1 Performance testing and accelerated testing in laboratory
 - Dr Terje F. Rønning, (HeidelbergCement Northern Europe, Norway)



- WP2 Performance testing and laboratory vs. field; Exposure site
 - Professor Benoît Fournier (Université Laval, Québec, Canada)



- O WP3 Performance testing; Assessment of detailed alkali inventory in concrete, including internal aggregate release, recycling and external supply.
 - Dr Esperanza Menéndez Méndez (Institute of Construction Science, "Eduardo Torroja" (CSIC), Spain)



- WP4 Verification of alkalis released from aggregates
 - Dr Klaartje De Weerdt (Norwegian University of Science and Technology, NTNU, Norway)




WP1 - Performance testing and accelerated testing in laboratory

Dr Terje F. Rønning (HeidelbergCement Northern Europe, Norway)

Develop performance test method(s):

- "RILEM AAR-10" (38°C concrete performance test)
 - 2017: Draft test procedure agreed
 - ullet Reduce leaching of alkalis ullet Increased prism size (100 mm)
 - - ${\bf 1.} \ \ {\bf Testing\ of\ } \underline{\bf specific\ aggregate\ combinations} \ {\bf together\ with\ various\ binder\ combinations}$
 - 2. Determination of general binder composition together with a "worst case" aggregate
 - Assessment of test results:









WP1 - Performance testing and accelerated testing in laboratory

- O Develop performance test method(s):
- "RILEM AAR-10"
 - 2018: Arrange Round Robin Test (RRT) (part of the Norwegian KPN-ASR project)
- On-going work on two (possible) alternative test procedures
 - ("RILEM AAR-11": 60°C concrete performance test)
 - (Japanese test procedure "TC-Draft of JCI-TC115FS-2013"; alkali wrapping)

O Validate alkali-boosting

- Ensure sufficient range of potential variations from the concrete constituents
- How much? (potential side effects?)
- Limited test program (part of the Norwegian KPN-ASR project)





WP3 - Performance testing; Assessment of detailed alkali inventory in concrete, including internal aggregate release, recycling and external supply



Dr Esperanza Menéndez Méndez (CSIC, Spain)

- O Develop a procedure for measuring alkali release from aggregates
- "RILEM AAR-8"
 - 2015: Draft test procedure agreed
 - 2016: RRT initiated (5 aggregates, 6 labs)
- O <u>STAR-report</u> on "alkali inventory" (on-going)

WP4 - Verification of alkalis released from aggregates [New activity 2017]

Dr Klaartje De Weerdt (NTNU, Norway)



- O Validate the test method for alkalis released by aggregates (AAR-8)
- <u>Verification</u> of potential alkali-release during lab. performance testing or in field structures

Draft topics:

- 1. How much of the total alkali from the cement is available in the pore solution?
- 2. Comparing methods to determine free alkali content? What is their accuracy?
- 3. Gathering results from on-going verification tests
- 4. Propose reference non-releasing aggregate for future studies

Meetings of RILEM TC 258-AAA



 1^{st} Meeting in Oslo $2^{nd} - 3^{rd}$ October 2014



3rd Meetings in Toronto 23rd - 25th September 2015



2nd Meeting in London 27th - 28th April 2015



4th Meeting in Paris 7th - 8th March 2016

